



RESULTS
REPORT :TURT150197732

Page 4 of 5
21 December ,2015

Test Method	Results	Requirements
-------------	---------	--------------

(*)Flame Propagation of Textiles and Films-Test Method 1

NFPA 701:2010

Face

Test Specification

Test Method: NFPA 701: 2010 Method 1
Criterion of ignition: 100 mm±10 mm high, methane gas flame applied 45 seconds
Sample Size: 150±5 mm x 400±5 mm
Side Tested: Face

Pre-treatment / Durability procedure

None (Because of the customer claimed that the sample has non durable finish)

Condition:

Prior to testing:
Conditioned for 30 minutes in an oven having a temperature 105±3 °C (220±5 °F)

<u>Time of burning material that falls to the bottom of the test chamber (s)</u>	<u>Weight before exposure (g)</u>	<u>Weight after exposure (g)</u>	<u>% Weight Loss</u>	<u>Observations on material</u>
--	-----------------------------------	----------------------------------	----------------------	---------------------------------

Specimen 1	0	19.488	17.786	8.7%	-
Specimen 2	0	19.464	17.336	10.9%	-
Specimen 3	0	19.492	16.737	14.1%	-
Specimen 4	0	19.583	17.513	10.6%	-
Specimen 5	0	19.658	16.925	13.9%	-
Specimen 6	0	19.894	17.479	12.1%	-
Specimen 7	0	19.769	19.003	3.9%	-
Specimen 8	0	19.722	18.917	4.1%	-
Specimen 9	0	19.739	19.697	0.2%	-
Specimen 10	0	19.914	17.544	11.9%	-
Average	0	19.672	17.894	9.04%	-
Standard Deviation	-	-	-	4.7346	-
			RESULT	PASS	PASS

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /ISTANBUL
Phone : +90 212 496 46 46 Fax: +90 212 452 80 55
e-mail : intertek@turkiye.intertek.com
<http://www.intertek-turkey.com>